

TECHNICAL DATA

Pattern Name	Pattern Prefix	Total Weight Oz/lin. Yd. 52/54" Width (Average)	Vinyl Weight Oz/lin. Yd. (Average)	Vinyl Weight Oz/sq. Yd. (Average)	Thickness Inches (Average)	Fabric Backing	Tensile Strength (Breaking) W X F (Average)	Tear Strength W X F (Average)	Specification Type	Flame Spread ASTM-E84	Smoke Developed ASTM-E84
Adria	AV2	20	13.3	10.5	0.018	Non-woven	61 X 58	39 X 50	II	15	20
Akura	A58	20	13.3	10.5	0.020	Osnaburg	95 X 90	30 X 31	II	25	15
Albero	A62	20	13.3	10.5	0.024	Non-woven	61 X 58	39 X 50	II	15	20
Alloy	A44	20	13.3	10.5	0.020	Osnaburg	95 X 90	30 X 31	II	25	15
Allusion	AV2	20	13.3	10.5	0.018	Non-woven	61 X 58	39 X 50	II	15	20
Allusion Silk	AV2	20	13.3	10.5	0.019	Osnaburg	95 X 90	30 X 31	II	25	15
Allusion Stripe	AV2	20	13.3	10.5	0.019	Osnaburg	95 X 90	30 X 31	II	25	15
Arbor	AV2	20	13.3	10.5	0.019	Osnaburg	95 X 90	30 X 31	II	25	15
Aries	A35	20	13.3	10.5	0.024	Osnaburg	95 X 90	30 X 31	II	25	15
Aristone	58	20	13.3	10.5	0.020	Osnaburg	95 X 90	30 X 31	II	25	15
Ashley	AV2	20	13.3	10.5	0.018	Non-woven	61 X 58	39 X 50	II	15	20
Ashley Stripe	AV2	20	13.3	10.5	0.019	Osnaburg	95 X 90	30 X 31	II	25	15
Bandon	AV3	20	13.3	10.5	0.018	Osnaburg	95 X 90	30 X 31	II	25	15
Baronness	AV2	20	13.3	10.5	0.018	Non-woven	61 X 58	39 X 50	II	15	20
Baronness Stripe	AV2	20	13.3	10.5	0.018	Non-woven	61 X 58	39 X 50	II	15	20
Bayboro	A71	20	13.3	10.5	0.024	Osnaburg	95 X 90	30 X 31	II	25	15
Bellagio	A27	20	13.3	10.5	0.028	Osnaburg	95 X 90	30 X 31	II	25	15
Bellagio	A68	20	13.3	10.5	0.028	Osnaburg	95 X 90	30 X 31	II	25	15
Biscayne	A82	20	13.3	10.5	0.019	Osnaburg	95 X 90	30 X 31	II	25	15
Bonaire	A69	20	13.3	10.5	0.023	Osnaburg	95 X 90	30 X 31	II	25	15
Botannica	A53	20	13.3	10.5	0.028	Osnaburg	95 X 90	30 X 31	II	25	15
Breccia	A45	20	13.3	10.5	0.024	Osnaburg	95 X 90	30 X 31	II	25	15

TECHNICAL DATA pg. 2

Pattern Name	Pattern Prefix	Total Weight Oz/lin. Yd. 52/54" Width (Average)	Vinyl Weight Oz/lin. Yd. (Average)	Vinyl Weight Oz/sq. Yd. (Average)	Thickness Inches (Average)	Fabric Backing	Tensile Strength (Breaking) W X F (Average)	Tear Strength W X F (Average)	Specification Type	Flame Spread ASTM-E84	Smoke Developed ASTM-E84
Caiman	A74	20	13.3	10.5	0.024	Osnaburg	95 x 90	30 x 31	II	25	15
Caribe	A47	14/15	10	8.3	0.014	Scrim	66 x 51	85 x 60	I	15	40
Carolina	A86	20	13.3	10.5	0.016	Osnaburg	95 x 90	30 x 31	II	25	15
Châteaux	A50	20	13.3	10.5	0.024	Osnaburg	95 x 90	30 x 31	II	25	15
Châteaux Stripe	A56	20	13.3	10.5	0.024	Osnaburg	95 x 90	30 x 31	II	25	15
Classico	A51	20	13.3	10.5	0.018	Osnaburg	95 x 90	30 x 31	II	25	15
Colonna	A80	20	13.3	10.5	0.020	Non-woven	61 x 58	39 x 50	II	15	20
Colori	A72	20	13.3	10.5	0.020	Osnaburg	95 x 90	30 x 31	II	25	15
Darnel	AV3	20	13.3	10.5	0.018	Osnaburg	95 x 90	30 x 31	II	25	15
DiLino	A22	20	13.3	10.5	0.022	Osnaburg	95 x 90	30 x 31	II	25	15
Djakard	A40	20	13.3	10.5	0.026	Osnaburg	95 x 90	30 x 31	II	25	15
Echelon	A61	20	13.3	10.5	0.020	Osnaburg	95 x 90	30 x 31	II	25	15
Encore	A57	20	13.3	10.5	0.018	Osnaburg	95 x 90	30 x 31	II	25	15
Filigrane	A42	20	13.3	10.5	0.020	Osnaburg	95 x 90	30 x 31	II	25	15
Fiori	AV2	20	13.3	10.5	0.019	Osnaburg	95 x 90	30 x 31	II	25	15
Flora	AV2	20	13.3	10.5	0.018	Non-woven	61 x 58	39 x 50	II	15	20
Florentino	AV1	15	10	8.3	0.013	Scrim	66 x 51	85 x 60	I	15	40
Galena	AV3	20	13.3	10.5	0.018	Osnaburg	95 x 90	30 x 31	II	25	15
Gentry	AV2	20	13.3	10.5	0.019	Osnaburg	95 x 90	30 x 31	II	25	15
Granada	A54	20	13.3	10.5	0.018	Osnaburg	95 x 90	30 x 31	II	25	15
Harlow	A77	20	13.3	10.5	0.019	Osnaburg	95 x 90	30 x 31	II	25	15
Hemisphere	N10	15	10	N/A	0.020	Non-woven	61 x 58	39 x 50	II	15	20

TECHNICAL DATA pg. 3

Pattern Name	Pattern Prefix	Total Weight Oz/lin. Yd. 52/54" Width (Average)	Vinyl Weight Oz/lin. Yd. (Average)	Vinyl Weight Oz/sq. Yd. (Average)	Thickness Inches (Average)	Fabric Backing	Tensile Strength (Breaking) W X F (Average)	Tear Strength W X F (Average)	Specification Type	Flame Spread ASTM-E84	Smoke Developed ASTM-E84
Hyde Park	A30	20	13.3	10.5	0.020	Osnaburg	95 x 90	30 x 31	II	25	15
Imari Block	A79	20	13.3	10.5	0.018	Non-woven	61 x 58	39 x 50	II	15	20
Inner Circle	A81	20	13.3	10.5	0.020	Non-woven	61 x 58	39 x 50	II	15	20
Intarsia Damask	N09	15	10	N/A	0.020	Non-woven	61 x 58	39 x 50	II	15	20
Kiawah	A78	20	13.3	10.5	0.021	Osnaburg	95 x 90	30 x 31	II	25	15
Kinsei	A60	20	13.3	10.5	0.024	Osnaburg	95 x 90	30 x 31	II	25	15
La Scala	A59	20	13.3	10.5	0.024	Osnaburg	95 x 90	30 x 31	II	25	15
Metallurgy	A55	20	13.3	10.5	0.018	Osnaburg	95 x 90	30 x 31	II	25	15
Mirabella	AV2	20	13.3	10.5	0.018	Non-woven	61 x 58	39 x 50	II	15	20
Moreno	A49	14/15	10	8.3	0.016	Scrim	66 x 51	85 x 60	I	15	40
Morinda	A36	20	13.3	10.5	0.020	Osnaburg	95 x 90	30 x 31	II	25	15
Nepal	A33	20	13.3	10.5	0.028	Osnaburg	95 x 90	30 x 31	II	25	15
Obol	A87	20	13.3	10.5	0.018	Osnaburg	95 x 90	30 x 31	II	25	15
Orlof	A88	20	13.3	10.5	0.018	Osnaburg	95 x 90	30 x 31	II	25	15
Osaka	A52	20	13.3	10.5	0.024	Osnaburg	95 x 90	30 x 31	II	25	15
Paglia	AV3	20	13.3	10.5	0.018	Osnaburg	95 x 90	30 x 31	II	25	15
Palisades	A70	20	13.3	10.5	0.019	Non-woven	61 x 58	39 x 50	II	15	20
Panama Linen	A76	20	13.3	10.5	0.021	Osnaburg	95 x 90	30 x 31	II	25	15
Pascha	A43	20	13.3	10.5	0.018	Osnaburg	95 x 90	30 x 31	II	25	15
Pembroke	AV2	20	13.3	10.5	0.018	Non-woven	61 x 58	39 x 50	II	15	20
Phidian	AV3	20	13.3	10.5	0.018	Osnaburg	95 x 90	30 x 31	II	25	15
Rhoton	AV3	20	13.3	10.5	0.018	Osnaburg	95 x 90	30 x 31	II	25	15

TECHNICAL DATA pg. 4

Pattern Name	Pattern Prefix	Total Weight Oz/lin. Yd. 52/54" Width (Average)	Vinyl Weight Oz/lin. Yd. (Average)	Vinyl Weight Oz/sq. Yd. (Average)	Thickness Inches (Average)	Fabric Backing	Tensile Strength (Breaking) W X F (Average)	Tear Strength W X F (Average)	Specification Type	Flame Spread ASTM-E84	Smoke Developed ASTM-E84
Rhythm	A75	20	13.3	10.5	0.025	Osnaburg	95 x 90	30 x 31	II	25	15
Sağri	A63	20	13.3	10.5	0.020	Osnaburg	95 x 90	30 x 31	II	25	15
Salerno	A67	20	13.3	10.5	0.025	Osnaburg	95 x 90	30 x 31	II	25	15
Seneca	A73	20	13.3	10.5	0.018	Osnaburg	95 x 90	30 x 31	II	25	15
Stria	AV2	20	13.3	10.5	0.019	Osnaburg	95 x 90	30 x 31	II	25	15
Styx	A84	20	13.3	10.5	0.020	Non-woven	61 x 58	39 x 50	II	15	20
Tangier	A46	25	16.5	14.6	0.027	Osnaburg	95 x 90	30 x 31	II	25	15
Tannery	A29	20	13.3	10.5	0.020	Osnaburg	95 x 90	30 x 31	II	25	15
Terreno	A85	20	13.3	10.5	0.016	Osnaburg	95 x 90	30 x 31	II	25	15
Toile	AV2	20	13.3	10.5	0.018	Non-woven	61 x 58	39 x 50	II	15	20
Topiary	A31	14/15	10	8.3	0.016	Scrim	66 x 51	85 x 60	I	15	40
Toulisse II	A34	20	13.3	10.5	0.024	Osnaburg	95 x 90	30 x 31	II	25	15
Umbria	A28	20	13.3	10.5	0.024	Osnaburg	95 x 90	30 x 31	II	25	15
Umbria	A83	20	13.3	10.5	0.019	Osnaburg	95 x 90	30 x 31	II	25	15
Westchester	A65	20	13.3	10.5	0.024	Osnaburg	95 x 90	30 x 31	II	25	15
Westchester Square	A64	20	13.3	10.5	0.025	Osnaburg	95 x 90	30 x 31	II	25	15
Zarick	AV3	20	13.3	10.5	0.018	Osnaburg	95 x 90	30 x 31	II	25	15

All Osnaburg 20 oz. backed wallcovering passes NFPA 286 Corner Burn
 Passes NFPA 101 Life Safety code